

MATERIAUX2018-2295

Aqueous N-Doped TiO₂ Catalysts for Visible Light Photocatalytic Applications

Julien Mahy*¹, Vincent Cerfontaine¹, Dirk Poelman², François Devred³, Eric Gaigneaux³, Benoît Heinrichs¹, Stéphanie Lambert¹

¹Departement of Chemical Engineering, Université de Liège, Liège, ²Lumilab, Department of Solid State Sciences, Université de Gand, Gand, ³Institute of Condensed Matter and Nanosciences—MOlecules, Solids and ReactiviTy (IMCN/MOST), Université catholique de Louvain, Louvain-La-Neuve, Belgique

Colloque, choix 1 :

Nanomatériaux, nanostructures et intégration dans les micro-systèmes

Colloque, choix 2 :

Matériaux poreux, granulaires et a grande aire spécifique

Colloque, choix 3 :

Eco-conception et recyclage

Vous souhaitez présenter votre travail sous format :

Oral uniquement

Votre résumé :

In this work, TiO₂ prepared with an aqueous sol-gel synthesis by peptization process is doped with nitrogen precursor to extend its activity towards the visible region. Three N-precursors are used: urea, ethylenediamine and triethylamine. Different molar N/Ti ratios are tested and the synthesis is adapted for each dopant. For urea- and trimethylamine-doped samples, anatase-brookite TiO₂ nanoparticles of 6–8 nm are formed, with a specific surface area between 200 and 275 m² g⁻¹. In ethylenediamine-doped samples, the formation of rutile phase is observed, and TiO₂ nanoparticles of 6–8 nm with a specific surface area between 185 and 240 m² g⁻¹ are obtained. X-ray photoelectron spectroscopy (XPS) and diffuse reflectance measurements show the incorporation of nitrogen in TiO₂ materials through Ti–O–N bonds allowing light absorption in the visible region. Photocatalytic tests on the remediation of water polluted with *p*-nitrophenol show a marked improvement for all doped catalysts under visible light. The optimum doping, taking into account cost, activity and ease of synthesis, is up-scaled to a volume of 5 L and compared to commercial Degussa P25 material. This up-scaled sample shows similar properties compared to the lab-scale sample, i.e., a photoactivity 4 times higher than commercial P25.

Mots clés : aqueous sol-gel process, multiple crystalline phase catalyst, N-doped TiO₂, photocatalysis, *p*-nitrophenol degradation

Conflicts d'intérêts : None Declared